PROWRAP-SA




MATERIAL: Polypropylene
COLOR: Red
COVERAGE: 400 Sqft

PRODUCT DESCRIPTION

Grip-Rite ProWrap®-SA is a self-adhering spunbonded polypropylene weather resistive barrier that is engineered to be vapor permeable, moisture protection barrier, and an air barrier for use in residential and commercial sidewall construction.

PRODUCT STRUCTURE



5-Layer Proprietary Construction

GRIP-RITE PROWRAP®-SA HAS BEEN TESTED TO MEET THE FOLLOWING MATERIAL STANDARDS:

- ICC-ES AC38
- Section 3.3: Physical Properties
- Section 3.5: Adhesion Performance per AAMA 711
- Section 3.6: Air Barrier Material per ASTM E2178
- Section 4.3: Drainage Efficiency per ASTM E2273
- Section 5.3.2, Exception 2: Flame Resistant per ASTM E1354 and ASTM E84

GRIP-RITE PROWRAP®-SA IS CERTIFIED TO FOLLOWING MATERIAL STANDARDS:

- ICC-ES AC38

GRIP-RITE PROWRAP®-SA CARRIES THE FOLLOWING CODE COMPLIANCE DOCUMENTATION:

- 2021 IBC/IRC Compliance: NEMO NER-PSBP-002 D4614250J



View Installation Instructions

PROPERTIES AND STANDARDS

PROPERTY	TEST STANDARD	GRIP-RITE PROWRAP®-SA
Thickness	ASTM D5147	19 mil
Dry breaking force	ASTM D3054	MD: 55 lbf; XMD: 45 lbf
Water resistance	ASTCC TM 127: 55-cm hydrostatic head for 5-hrs.	Control and weathered: No leakage
Water vapor transmission/permeance	ASTM E96, Procedure A (desiccant)	WVT: 411 g/m2 per 24 hrs
		Permeance: 46 perms
Low temperature flexibility	AC38, Section 3.3.4	No cracks at 20˚F
90-degree peel adhesion	AAMA 711, Section 5.3	> 1.5 lbf/in Anodized aluminum, DensGlass® Sheathing, OSB, plywood, vinyl and its own facing
Accelerated UV aging	AAMA 711, Section 5.4: 336-hours, ASTM G154, Cycle 1	No visual damage and maintain adhesion performance over anodized aluminum
Elevated temperature exposure	AAMA 711, Section 5.5: Level 3 (7-days at 176˚F)	No visual damage and maintain adhesion performance over anodized aluminum
Thermal cycling	AAMA 711, Section 5.6: 10 cycles of 8-hrs. at 120˚F and 16-hrs. at -40˚F	No visual damage and maintain adhesion performance over anodized aluminum
Water immersion	AAMA 711, Section 5.8: 7 days immersion at 73˚F	No visual damage and maintain adhesion performance over anodized aluminum
Resistance to peeling from itself	AAMA 711, Section 5.9: Level 1 (7-days at 122˚F)	No visible damage, bond loss, buckling or rippling
Sealability around nail	AAMA 711, Sections 5.2.1 and 5.2.2; ASTM D7349, Protocol 4 per D1970	Control and after thermal cycling: No leakage
Air leakage rate	ASTM E2178	0.02 L/s-m2 at 75 Pa
Drainage efficiency	ASTM E2273 per AC38, Section 4.3	> 90% efficiency
Fire test response	ASTM E1354	Heat release rate: 143 kW/m2
		Total heat released: 5 MJ/m2
		Effective heat of combustion: 18 MJ/kg
Surface burning characteristics	ASTM E84	Flame Spread Index (FSI): 0
		Smoke Developed Index (SDI): 40

PRODUCT

SKU	SIZE		COLOR	WEIGHT/ ROLL	PAL/ QTY	PAL/ TRUCK	ROLLS/ TRUCKLOAD
	AREA	DIMENSIONS					
HWPRO4100SA	4sq	4x100	Red	19lbs	36	38	1368

PRIMESOURCE BUILDING PRODUCTS, INC.
A PrimeSource® Brands Company | PSB PRIMESOURCE BRANDS

Contact your PrimeSource® Building Products representative to order today.
800-676-7777 | primesourcebp.com

DB211376i
NEMO|cert.

Grip-Rite ProWrap®-SA *is exclusively distributed by* ***PrimeSource® Building Products, Inc.*** *1321 Greenway Drive, Irving, TX 75038-2504.*
Visit ***grip-rite.com*** *or call 800-676-7777 for details, warranty information and limitations. Pricing and availability are subject to change without notice.*
© 2026 PrimeSource® Building Products, Inc. All Rights Reserved.